

**FORMULA:**  $C_6H_4(COO-C_8H_{17})_2$

**MOL WT:** 390.54

**DESCRIPTION**

Virtually colorless, oily liquid, insoluble in water, miscible with mineral oils.

**APPLICATIONS**

As plasticizer in PVC and other polymeric compounds (such as PVCA y CAB) used in shoe industry, textiles, and plastic laminates, plastisoles, sealants, pipe and profiles, hoses, films, cable coatings and automotive accessories. Also used as plasticizer in SBR compounds.

**SPECIFICATIONS**

**TEST METHOD**

Appearance	Clear and virtually free of suspended matter		Visual
Purity, wt. %	99.0	Min.	MP-500
Acidity as Phthalic acid, wt. %	0.01	Max.	MP-501
Color, Pt-Co	25	Max.	MP-502
Water, wt %	0.1	Max.	MP-400
Flash Point, °C <sup>(1)</sup>	209	Min.	MP-504
Refractive index, $n_D$ 20 °C	1.4855	Min.	MP-505
	1.4875	Max.	
Specific gravity, 25/25 °C	0.980	Min.	MP-506
	0.985	Max.	

**Notes:**

(1) Flash Point is referred at sea level. Cleveland Open Cup.

**AVAILABILITY**

In bulk or metallic drums, containing 200 kg, net wt. (441 lb. net) or containers 1 t, net wt.



Unidad Industrial Tlaxcala

## SALES SPECIFICATION

EVC-021

DIOCTYL PHTHALATE  
INDUSTRIAL GRADE

06/05/20

2 of 2

Revision

11

**Headquarters:** Bosque de Radiatas No. 34, Bosques de las Lomas, Cuajimalpa de Morelos, C.P. 05120, CDMX, Tel. 2789-2200  
Fax: 2789-2351

**TLAXCALA Plant:** km 154 Carretera México-Veracruz vía Texcoco, Corredor Industrial San Cosme Xaloztoc, Tlaxcala, C.P. 90460

### Website

[www.grupoidesa.com](http://www.grupoidesa.com)

### Email

**Commercial:** [pedidosidesa@idesa.com.mx](mailto:pedidosidesa@idesa.com.mx)      **Quality:** [calidesa@idesa.com.mx](mailto:calidesa@idesa.com.mx)